



ANALYTICAL REPORT

PREPARED FOR

Attn: Jorge Quinones
Irrigation Express
13650 Vaughn Street
San Fernando, California 91340

Generated 5/1/2023 1:00:02 PM

JOB DESCRIPTION

BEL AIR LIGHT-73

JOB NUMBER

860-47517-1

Client Sample Results

Client: Irrigation Express
Project/Site: BEL AIR LIGHT-73

Job ID: 860-47517-1

Client Sample ID: BEL AIR LIGHT-73

Lab Sample ID: 860-47517-1

Date Collected: 04/18/23 11:20

Matrix: Solid

Date Received: 04/21/23 10:57

Method: SW846 6020A - Metals (ICP/MS)

Analyte	Result	Qualifier	RL	Unit	D	Prepared	Analyzed	Dil Fac
Lead	<1.96	U	1.96	mg/Kg		04/25/23 21:56	04/26/23 21:48	10

1

2

3

4

5

6

7

8

9

10

11

12

13

14

15

QC Sample Results

Client: Irrigation Express
 Project/Site: BEL AIR LIGHT-73

Job ID: 860-47517-1

Method: 6020A - Metals (ICP/MS)

Lab Sample ID: MB 860-100396/1-A
Matrix: Solid
Analysis Batch: 100581

Client Sample ID: Method Blank
Prep Type: Total/NA
Prep Batch: 100396

Analyte	MB Result	MB Qualifier	RL	Unit	D	Prepared	Analyzed	Dil Fac
Lead	<0.200	U	0.200	mg/Kg		04/25/23 21:53	04/26/23 20:32	1

Lab Sample ID: LCS 860-100396/2-A
Matrix: Solid
Analysis Batch: 100581

Client Sample ID: Lab Control Sample
Prep Type: Total/NA
Prep Batch: 100396

Analyte	Spike Added	LCS Result	LCS Qualifier	Unit	D	%Rec	%Rec Limits
Lead	10.0	9.852		mg/Kg		99	80 - 120

Lab Sample ID: LCSD 860-100396/3-A
Matrix: Solid
Analysis Batch: 100581

Client Sample ID: Lab Control Sample Dup
Prep Type: Total/NA
Prep Batch: 100396

Analyte	Spike Added	LCSD Result	LCSD Qualifier	Unit	D	%Rec	%Rec Limits	RPD	RPD Limit
Lead	10.0	9.940		mg/Kg		99	80 - 120	1	20



Environment Testing
Xenco

CERTIFICATE OF ANALYSIS

Client: Irrigation Express
Product: Bel Air Light-73
Eurofins Sample #:860-47517-1
Lead Results: Less than 1.96 part per million

Synthetic fibers from turf product Bel Air Light-73, taken by Irrigation Express on 04/18/2023, and received by Eurofins Labs, 04/21/2023, were analyzed by Eurofins Labs for total lead by method SW6020A. The results were less than 1.96 milligrams lead per kilogram synthetic fiber (<1.96 mg/kg).

Dr. Blair Leftwich, Director

Date